

EVERNOX[®]-B210

EVERNOX[®]-B210GF



Synergistic Processing and Long-Term Thermal Stabilization

Chemical Name 66.7% EVERFOS-168 : Tris (2,4-di-tert-butylphenyl) phosphite

33.3% EVERNOX-10 : Pentaerythritol Tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate)

Formula 66.7% C₄₂H₆₃O₃P (EVERFOS-168)
33.3% C₇₃H₁₀₈O₁₂ (EVERNOX-10)

Structure



Molecular Weight 646.9

1178

CAS Number 31570-04-4

6683-19-8

Specification

Criterion

Requirement

Appearance

White, free-flowing powder for EVERNOX-B210
White, free-flowing granules for EVERNOX-B210GF

Ash content

0.1% max

Volatiles

0.5% max

Clarity of solution
(10g in 100ml toluene)

Clear solution

Transmittance
(10g in 100 ml toluene)

at 425 nm 97.0% min
at 500 nm 97.0% min

Assay

EVERFOS-168 64.6~68.6%
EVERNOX-10 31.4~35.4%

Physical Properties

Melting range (°C)

110-186°C

Flash point (°C)

>150°C

Applications	EVERNOX-B210 and EVERNOX-B210GF are used in polyolefins and olefins-copolymers such as LDPE, HDPE, LLDPE, PP and EVA. It can also be used in other polymers such as engineering plastics, styrene homo and copolymers such as PBT, PET, PA, POM, PS, ABS, PUR, elastomers BR, SBR, SBS, adhesives and other organic substrates. The B-blends can be used in combination with light stabilizers of UV-absorbers and hindered amine light stabilizers.
Recommendation for use	In polyolefins, the dosage levels for EVERNOX-B210 and EVERNOX-B210GF are between 0.1% to 0.25%, depending on polymers and processing conditions. The optimum level is various of application specific needs.
Handling & Safety	EVERNOX-B210 and EVERNOX-B210GF should be handled with care and prevent contamination of the environment. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.
Packing	The following packages are available upon customer's request : (1) 20 kgs×2 PE bags in the carton box. (2) 25 kgs ×2 PE bags in the carton box. (3) 50 kgs fiber drum. (4) Other specific request.
Transportation	EVERNOX-B210 and EVERNOX-B210GF are not dangerous materials according to the transportation regulations.
Storage	EVERNOX-B210 and EVERNOX-B210GF should be stored under suitable conditions (dry & cool). Maximum recommended storage temperature under 45°C and the storage time from the date of analysis : 24 months.



妙春實業股份有限公司
EVERSPRING CHEMICAL CO., LTD.

台中市工業區 24 路 4 號

4, 24th Road, Industrial Park, Taichung, Taiwan

Tel : +886-4-23592448 Fax : +886-4-23593163

E-mail : sales@everspringchem.com.tw

Web site : www.everspringchem.com