


# EVERSTAB LS-622

Polymeric sterically hindered amine derivative

**Chemical Name** Poly(N-Beta-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxy-piperidyl-succinate)

**Product Name** Poly(4-hydroxy-2,2,6,6-tetramethyl-1-piperidine ethanol-alt-1,4-butanedioic acid)

**Structure**



**Molecular Weight** 3100-4000

**CAS Number** 65447-77-0

<b>Specification</b>	<u>Criterion</u>	<u>Requirement</u>
	Appearance	White to light yellow crystalline powder
	Melting range	55-70°C
	Loss on drying	0.5% max
	Color of solution (5g/100ml Toluene)	at 425 nm 97.0% min
	Transmittance	at 450 nm 99.0% min
	Ash	0.1% max

**Package** 25kgs Net/Carton

**Application** Main applications are Polyolefin (PP,PE), Olefin copolymers such as EVA as well as blends of Polypropylene with Elastomers.  
It is also highly effective in Polyacetals, Polyamides and Polyurethane applications.



**妙春實業股份有限公司**  
**EVERSPRING CHEMICAL CO., LTD.**

台中市工業區 24 路 4 號

4, 24<sup>th</sup> Road, Industrial Park, Taichung, Taiwan

Tel : +886-4-23592448 Fax : +886-4-23593163

E-mail : [sales@everspringchem.com.tw](mailto:sales@everspringchem.com.tw)

Web site : [www.everspringchem.com](http://www.everspringchem.com)