



SUNSORB LS-119

SUNSORB LS-119GF

Chemical Name 1,3,5-Triazine-2,4,6-triamine,N,N''-[1,2-ethane-diyl-bis[[[4,6-bis-[butyl(1,2,2,6,6-pentamethyl-4-piperidiny]amino)-1,3,5-triazine-2-yl]imino]-3,1-propanediyl]] bis [N',N''-dibutyl-N',N''-bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-

Structure



Molecular Weight 2286

CAS Number 106990-43-6

Specification	<u>Criterion</u>	<u>Requirement</u>
	Appearance	White to light yellow crystalline powder or granular
	Melting point	115-150°C
	Volatiles(10g/2hr/100°C)	1.0% max
	Color of solution (Transmission)	425 nm(10% w/v Toluene) : 90.0% min 450 nm(10% w/v Toluene) : 93.0% min 500 nm(10% w/v Toluene) : 95.0% min
	Ash	0.1% max

Applications Sunorb LS-119 is particularly effective in polypropylene, polyethylene, α -olefin copolymers and blends with EPR, ERR, PE, EVA, EAA, EVOH and filled PP.

Packing Granular : 40 kg/Drum、 20kg/Box
Powder : 30 kg/Drum.



妙春實業股份有限公司
EVERSPRING CHEMICAL CO., LTD.

台中市工業區 24 路 4 號

4, 24Rd., Industrial Park, Taichung, Taiwan

Tel : +886-4-23592448 Fax : +886-4-23593163

E-mail : everspring@seed.net.tw

Web site : everspringchem.com.tw