**EVERNOX-76** 

CH2CH2COOC18H37

(CH<sub>3</sub>)<sub>3</sub>C

HO

(CH<sub>3</sub>)<sub>3</sub>C

Requirement

0.1% max

0.5% max

Clear solution

at 425 nm

at 500 nm 97.0% min

EVERFOS-168 64.6~68.6% EVERNOX-76 31.4~35.4%

531

97.0% min

2082-79-3

White, free-flowing powder for EVERNOX-B201

White, free-flowing granules for EVERNOX-B201GF

## EVERNOX<sup>®</sup>-B201 EVERNOX<sup>®</sup>-B201GF

Synergistic Processing and Long-Term Thermal Stabilization

**Chemical Name** 67% EVERFOS-168: Tris (2,4-di-tert-butylphenyl) phosphate


33% EVERNOX-76: Octadecyl-3-(3,5-di-tert-4-hydroxyphenyl)-propionate

Formula

 $\begin{array}{c} 67\% \ C_{42}H_{63}O_{3}P \\ 33\% \ C_{35}H_{62}O_{3} \end{array}$ 

Structure

EVERFOS-168



Molecular Weight

CAS Number

Specification

<u>Criterion</u> Appearance Ash content

31570-04-4

646.9

Volatiles Clarity of solution (10g in 100ml toluene) Transmittance


(10g in 100 ml toluene) Assay

**Physical Properties** 

Melting range (°C)	49-187°C
Flash point (°C)	>150°C

Applications EVERNOX-B201 and EVERNOX-B201GF are used in polyolefins and olefins-copolymers such as LDPE, HDPE, LLDPE, PP and EVA. It can also be used in other polymers such as engineering plastics, styrene homo and copolymers such as PBT, PET, PA, POM, PS, ABS, PUR, elastomers BR, SBR, SBS, adhesives and other organic substrates. The B-blends can be used in combination with light stabilizers of UV-absorbers and hindered amine light stabilizers.

Recommendation for use	In polyolefins, the dosage levels for EVERNOX-B201 and EVERNOX-B201GF are between 0.1% to 0.25%, depending on polymers and processing conditions. The optimum level is various of application specific needs.
Handling & Safety	EVERNOX-B201 and EVERNOX-B201GF should be handled with care and prevent contamination of the environment. Avoid dust formation and ignition sources.
	For more detailed information please refer to the material safety data sheet.
Packing	<ul> <li>The following packages are available upon customer's request :</li> <li>(1) 20 kgs×2 PE bags in the carton box.</li> <li>(2) 25 kgs×2 PE bags in the carton box.</li> <li>(3) 50 kgs fiber drum.</li> <li>(4) Other specific request.</li> </ul>
Transportation	EVERNOX-B201 and EVERNOX-B201GF are not dangerous materials according to the transportation regulations.
Storage	EVERNOX-B201 and EVERNOX-B201GF should be stored under suitable conditions (dry & cool). Maximum recommended storage temperature under $45^{\circ}$ C and the storage time from the date of analysis : 24 months.



**妙春實業股份有限公司 EVERSPRING CHEMICAL CO., LTD.** 台中市工業區 24 路4號 4, 24Rd., Industrial Park, Taichung, Taiwan Tel:+886-4-23592448 Fax:+886-4-23593163 E-mail: sales@everspringchem.com.tw Web site:www.everspringchem.com