

EVERNOX®-B401 EVERNOX®-B401GF

Synergistic Processing and Long-Term Thermal Stabilization

Chemical Name 80% EVERFOS-168: Tris (2,4-di-tert-butylphenyl) phosphite

20% EVERNOX-76: Octadecyl-3-(3,5-di-tert-4-hydroxyphenyl)-propionate

Formula 80% C₄₂H₆₃O₃P

20% C₃₅H₆₂O₃

Structure EVERFOS-168 EVERNOX-76

$$(CH_3)_3C$$

$$C (CH_3)_3C$$

$$C (CH_3)_3C$$

$$C (CH_3)_3C$$

$$C (CH_3)_3C$$

$$C (CH_3)_3C$$

$$C (CH_3)_3C$$

Molecular Weight 646.9 531

CAS Number 31570-04-4 2082-79-3

Specification <u>Criterion</u> <u>Requirement</u>

Appearance White, free-flowing powder for EVERNOX-B401

White, free-flowing granules for EVERNOX-B401GF

Ash content 0.1% max
Volatiles 0.5% max
Clarity of solution Clear solution

(10g in 100ml toluene)

Transmittance at 425 nm 97.0% min (10g in 100 ml toluene) at 500 nm 97.0% min

Assay EVERFOS-168 78.0~82.0% EVERNOX-76 18.0~22.0%

Physical Properties

Melting range (°C) 49-187°C Flash point (°C) >150°C

Applications EVERNOX-B401 and EVERNOX-B401GF are used in polyolefins and olefins-copolymers

such as LDPE, HDPE, LLDPE, PP and EVA. It can also be used in other polymers such as engineering plastics, styrene homo and copolymers such as PBT, PET, PA, POM, PS, ABS, PUR, elastomers BR, SBR, SBS, adhesives and other organic substrates. The B-blends can be used in combination with light stabilizers of UV-absorbers and hindered amine light stabilizers.

Recommendation for use

In polyolefins, the dosage levels for EVERNOX-B401 and EVERNOX-B401GF are between 0.1% to 0.25%, depending on polymers and processing conditions. The optimum level is various of application specific needs.

Handling & Safety

EVERNOX-B401 and EVERNOX-B401GF should be handled with care and prevent contamination of the environment. Avoid dust formation and ignition sources.

For more detailed information please refer to the material safety data sheet.

Packing

The following packages are available upon customer's request:

- (1) 20 kgs×2 PE bags in the carton box.(2) 25 kgs×2 PE bags in the carton box.
- (3) 50 kgs fiber drum.(4) Other specific request.

Transportation

EVERNOX-B401 and EVERNOX-B401GF are not dangerous materials according to the transportation regulations.

Storage

EVERNOX-B401 and EVERNOX-B401GF should be stored under suitable conditions (dry & cool). Maximum recommended storage temperature under 45°C and the storage time from the date of analysis: 24 months.



妙春實業股份有限公司 EVERSPRING CHEMICAL CO., LTD.

台中市工業區 24路4號

4, 24Rd., Industrial Park, Taichung, Taiwan

Tel: +886-4-23592448 Fax: +886-4-23593163

E-mail: sales@everspringchem.com.tw Web site: www.everspringchem.com